



Technical Data Sheet Renewable Polyester Polyols

MYRINOL™ DGTB-56 POLYESTER POLYOL For Foams

DERIVED FROM BIO-BASED SUCCINIC ACID, DIETHYLENE GLYCOL, AND PEG

CAS No. 380894-87-1

DGTB-56 developmental polyester polyol is a branched polyester polyol based on bio-derived succinic acid, diethylene glycol and polyethylene glycol that provides high renewable content and good properties for foams. As with any product, the performance of DGTB-56 polyol in any application must be verified by the end user.

Product Properties	Value
Hydroxyl number	64
Functionality	2.7
Viscosity (60 °C, cPs)	4000
Moisture (wt%)	0.01
Acid Value	1.2
Color (APHA)	480
Bio-Based Carbon Content (%)	47

Storage and Handling

DGTB-56 developmental polyester polyol is hygroscopic and may absorb water. Containers should be kept tightly closed and protected from contamination especially by moisture. The product should be stored in a cool, dry location. The product may be heated prior to use to reduce the viscosity for processing.

Health and Safety Information

Before working with this product, read and become familiar with the hazards, proper use, and handling characteristics of the product. When using this product, the information and advice given in the Safety Data Sheet should be observed. Normal precautions for the handling of chemicals, including wearing proper personal protective equipment, should be followed at all times. A Safety Data Sheet is available on request.

Packaging

Samples are available in 1-gallon cans or 55-gallon steel drums.

Contact Information

Please contact GC Innovation America at products@gcinnovationamerica.com, or call 617-657-5200 for more information.

42 Cummings Park, Woburn MA, 01801
Tel: 617-657-5200 Fax 617-657-5210 Web: www.gcinnovationamerica.com

The information presented on this technical data sheet does not constitute a warranty of performance or of fitness for any specific application, and is subject to change without notice. No license under any patent is implied or granted.



Technical Data Sheet Renewable Polyester Polyols

Revised November 29, 2012

42 Cummings Park, Woburn MA, 01801
Tel: 617-657-5200 Fax 617-657-5210 Web: www.gcinnovationamerica.com

The information presented on this technical data sheet does not constitute a warranty of performance or of fitness for any specific application, and is subject to change without notice. No license under any patent is implied or granted.